



## ROWALIT® 200-13

### Copolyamide - Powder

<b>Type</b>	Copolyamide
<b>Melting range / °C DSC</b>	120 - 130
<b>Melting viscosity / g</b>	
MFI 160°C, 2.16 kg, 10 min.	23
<b>Chemical Basis</b>	CoPA/CopES Blend
<b>Powder sizes</b>	
Pastedot	✓
Doubledot	✓
Powderdot	✓
Scatter	✓
Granules	✗
<b>Resistance to dry cleaning</b>	very good
<b>Washing resistance</b> in °C	80°C
<b>Steam resistance</b>	good
<b>Heat resistance</b> in °C	110
<b>Fusing conditions with flow-through-press</b>	
Lamination temperature in °C	130 - 150
Pneumatic pressure N / cm <sup>2</sup>	3 - 5
Time in sec.	12 - 20
<b>Appearance</b>	White powder

### Application

Interlinings with high wash resistance; technical bondings with good process temperature and fastness relation; comply to high requirements

- 1 -

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.



Version: 27.09.2021

- 2 -

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.

ROWAK AG  
Hadlaubstraße 66 Tel +41 43 300 53 33 [www.rowak.ch](http://www.rowak.ch)  
CH 8006 Zürich Fax +41 43 300 53 35 [info@rowak.ch](mailto:info@rowak.ch)

Certified Quality  
Management System

ROWAK AG  
Schmittenstraße 21  
D-79771 Klettgau

