



ROWALIT® 600-1

Polypropylene - Powder

Type	Polypropylen
Melting range / °C DSC	132 - 136
Melting viscosity / g	
MFI 190°C, 2.16 kg, 10 min.	4
Density	0.895
Powder sizes	
Pastedot	✓
Doubledot	✓
Powderdot	✓
Scatter	✓
Granules	✓
Resistance to dry cleaning	
Heat resistance in °C	115
Fusing conditions with flow-through-press	
Lamination temperature in °C	140 - 180
Pneumatic pressure N / cm ²	3 - 6
Time in sec.	12 - 30
Appearance	Pellets, Powder

Application

Engine compartment isolations, Carpet backings, Headliner, Rear shelf, Nonwovens

Version: 27.09.2021

- 1 -

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.

Certified Quality
Management System

