



## ROWALIT® 400-14

### Copolyester - Powder

<b>Type</b>	Copolyester
<b>Melting range / °C DSC</b>	177 - 186
<b>Melting viscosity / g</b>	
MFI 190°C, 2.16 kg, 10 min.	110
<b>Chemical Basis</b>	Copolyester
<b>Powder sizes</b>	
Pastedot	✓
Doubledot	✓
Powderdot	✓
Scatter	✓
Granules	✓
<b>Heat resistance</b> in °C	140
<b>Fusing conditions with flow-through-press</b>	
Lamination temperature in °C	210 - 230
Pneumatic pressure N / cm <sup>2</sup>	3 - 10
Time in sec.	12 - 20

## Application

Bondings in filtration systems - Lubricants / Oils / Fuels

Version: 27.09.2021

- 1 -

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.

