

# ROWAFLEX® X 572

## Emulsifier for thermoplastic adhesives

<b>Type</b>	Emulsifier
<b>Chemical character</b>	Long-chain ethoxylated fatty alcohol
<b>Density</b>	96 kg/m <sup>3</sup>
<b>pH value</b>	7
<b>Ionogenity</b>	non-ionic
<b>Appearance</b>	Clear to cloudy liquid
<b>Product viscosity</b>	90 mPa.s (EN 12092 Brookfield (23°C/60rpm))
<b>Properties</b>	<p>ROWAFLEX® X 572 is an emulsifier for all common thermoplastic powders like copolyamides, copolyester, high-and low density polyethylene and polyurethane. It has highly efficient dispersing properties.</p> <p>Pastes with ROWAFLEX® X 572</p> <ul style="list-style-type: none"> <li>• are easy and fast to prepare</li> <li>• are having excellent running properties</li> <li>• are free of organic solvents and enviromentalfriendly</li> <li>• provides good adhesion values for different fabrics</li> <li>• due to the good dispersing properties only low quantity is required</li> </ul>
<b>Application</b>	<p>ROWAFLEX® X 572 is a high efficient emulsifier for thermoplastic hotmelt powders.</p> <p>For 100 kg ready made paste (35 % solid content) only 1 kg of ROWAFLEX® X 572 is required. It is easy and fast disperable in cold water.</p>

Version: 03.05.2022

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.

ROWAK AG  
Hadlaubstraße 66 Tel +41 43 300 53 33 www.rowak.ch  
CH 8006 Zürich Fax +41 43 300 53 35 info@rowak.ch

Certified Quality  
Management System

ROWAK AG  
Schmittenstraße 21  
D-79771 Klettgau

