ROWALIT 1009

Polyethylene-Ethylenevinylacetate - Powder

07.09.2026
info@rowak.ch

Product name	ROWALIT™ 1009
Type	Copolymer Blend
Chemical character	Special low viscosity thermoplastic
Melting range	65 – 110 °C DSC
Melt Flow Index	90 g / 10 Min. (MFI 190°C / 2,16 kg)
Powder sizes	Scatter (0 – 400 µm, 0 – 500 µm) Other sizes upon request
Heat resistance	70 °C
Typical application	Techn. bondings, Under-tile and shuttering layers, etc.
Appearance	White powder
Ratio of renewable raw materials	0 %
Biodegradability	no
Fusing conditions with flow-through-press	Lamination temperature: 120 – 135 °C Pneumatic pressure: 2 – 5 N/cm² Time: 8 – 10 Sekunden
Application	Techn. bondings / laminations, Under-tile and shuttering layers, etc.

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntisse und Erfahrungen. Wir beraten Sie damit Unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

ROWAK
SWISS ENGINEERED ADHESIVES

ROWAK AG
Hadlaubstrasse 66
8006 Zürich
Switzerland

ROWAK AG
Schmittenstrasse 21
79771 Klettgau-Griessen
Germany

ISO 9001