

ROWALIT® 200-11

Copolyamide - Powder

Type	Copolyamide
Chemical character	Copolyamide
Melting range	105 – 115 °C DSC
Melt Flow Index	20 g / 10 Min. (MFI 160°C / 2,16 kg)
Powder sizes	Pastedot (0 – 63 µm, 0 – 80 µm) Doubledot (80 – 200 µm) Powderdot Scatter (100 – 500 µm) Granules Other sizes upon request
Washing resistance	60 °C
Dry cleaning resistance	very good
Heat resistance	100 °C
Hand iron	no
Steam resistance	good
Appearance	White powder
Ratio of renewable raw materials	0 %
Biodegradability	no
Fusing conditions with flow-through-press	Lamination temperature: 120 – 140 °C Pneumatic pressure: 3 – 5 N/cm ² Time: 10 – 15 seconds
Application	Adhesive polymer powder with broad application area, standard quality; techn. bondings / laminates Labelprint, Digitalprint, Flocking

Version: 28.06.2022

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.