

ROWALIT® 200-13

Copolyamide/Copolyester - Powder

Type	Copolyamide
Chemical character	COPA/COPEs Blend
Melting range	120 – 130 °C DSC
Melt Flow Index	23 g / 10 Min. (MFI 160°C / 2,16 kg)
Powder sizes	Pastedot (0 – 80 µm) Doubledot (80 – 200 µm) Powderdot (0 – 200 µm) Scatter (100 – 500 µm) Other sizes upon request
Washing resistance	80 °C
Dry cleaning resistance	very good
Heat resistance	110 °C
Hand iron	no
Enzyme washing	no
Steam resistance	moderate
Appearance	White powder
Ratio of renewable raw materials	0 %
Biodegradability	no
Fusing conditions with flow-through-press	Lamination temperature: 130 – 150 °C Pneumatic pressure: 3 – 5 N/cm ² Time: 12 – 20 seconds
Application	Interlinings with high wash resistance; technical bondings with good process temperature and fastness relation; comply to high requirements.

Version: 28.06.2022

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.