

ROWALIT® 200-14

Copolyamide - Powder

Type	Biobased Products, Copolyamide
Chemical character	Copolyamid
Melting range	110 – 120 °C DSC
Melt Flow Index	30 g / 10 Min. (MFI 160°C / 2,16 kg)
Powder sizes	Pastedot Doubledot Powderdot Scatter (0 – 500 µm) Granules Other sizes upon request
Washing resistance	60 °C
Dry cleaning resistance	good
Heat resistance	100 °C
Typical application	Technical Bondings
Hand iron	no
Appearance	White powder
Ratio of renewable raw materials	38 %
Biodegradability	no
Fusing conditions with flow-through-press	Lamination temperature: 120 – 150 °C Pneumatic pressure: 3 – 5 N/cm ² Time: 12 – 20 seconds
Application	Interlinings, technical bondings

Version: 28.06.2022

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.