

ROWALIT 200-16

Copolyamide - Powder

Type	Biobased Products, Copolyamide
Chemical character	Copolyamid
Melting range	110 – 120 °C DSC
Melt Flow Index	40 g / 10 Min. (MFI 160°C / 2,16 kg)
Powder sizes	Pastedot (0 – 80 µm) Doubledot (80 – 200 µm) Powderdot Scatter Granules Other sizes upon request
Washing resistance	60 °C
Dry cleaning resistance	very good
Heat resistance	100 °C
Appearance	White powder
Ratio of renewable raw materials	42 %
Biodegradability	no
Fusing conditions with flow-through-press	Lamination temperature: 120 – 140 °C Pneumatic pressure: 3 – 5 N/cm ² Time: 10 – 18 seconds
Application	Interlinings with broad application area, technical bondings

Version: 10.01.2025

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.