

# ROWALIT® 200-42

## Copolyamide - Powder

<b>Type</b>	Copolyamide
<b>Chemical character</b>	Copolyamid
<b>Melting range</b>	105 – 125 °C DSC
<b>Melt Flow Index</b>	40 g / 10 Min. (MFI 160°C / 2,16 kg)
<b>Powder sizes</b>	Pastedot (0 – 80 µm) Doubledot (80 – 200 µm) Powderdot Scatter Granules Other sizes upon request
<b>Washing resistance</b>	60 °C
<b>Dry cleaning resistance</b>	very good
<b>Heat resistance</b>	60 °C
<b>Hand iron</b>	no
<b>Steam resistance</b>	moderate
<b>Stone-wash resistance</b>	no
<b>Appearance</b>	White powder
<b>Ratio of renewable raw materials</b>	0 %
<b>Biodegradability</b>	no
<b>Fusing conditions with flow-through-press</b>	Lamination temperature: 130 – 150 °C Pneumatic pressure: 3 – 5 N/cm <sup>2</sup> Time: 10 – 15 seconds
<b>Application</b>	Interlinings with broad application area, technical bondings

Version: 28.06.2022

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.  
All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.