

ROWALIT® 200-51

Copolyamide - Powder

Type	Copolyamide
Chemical character	Copolyamide
Melting range	125 – 135 °C DSC
Melt Flow Index	25 g / 10 Min. (MFI 160°C / 2,16 kg)
Powder sizes	Pastedot (0 – 80 µm) Doubledot Granules Other sizes upon request
Washing resistance	95 °C
Dry cleaning resistance	very good
Heat resistance	115 °C
Typical application	Interlining for Denim, techn. bondings / laminations
Hand iron	no
Enzyme washing	yes
Steam resistance	very good
Stone-wash resistance	yes
Appearance	White powder
Ratio of renewable raw materials	0 %
Biodegradability	no
Fusing conditions with flow-through-press	Lamination temperature: 140 – 160 °C Pneumatic pressure: 3 – 5 N/cm ² Time: 10 – 20 seconds
Application	Adhesive Powder for bondings with high thermal stability and wash resistance such as interlinings for Denim/Jeans and Enzyme-wash applications; Technical bondings for difficult to fuse substrates

Version: 28.06.2022

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.
All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.

ROWAK AG
Hadlaubstraße 66 Tel +41 43 300 53 33 www.rowak.ch
CH 8006 Zürich Fax +41 43 300 53 35 info@rowak.ch

Certified Quality
Management System

ROWAK AG
Schmittenstraße 21
D-79771 Klettgau

