

ROWALIT® 200-63

Copolyamide

Type	Copolyamide
Chemical character	Copolyamide
Melting range	100 – 120 °C DSC
Melt Flow Index	180 g / 10 Min. (MFI 160°C / 2,16 kg)
Powder sizes	Pastedot (0 – 80 µm) Doubledot (80 – 200 µm) Scatter Granules
Washing resistance	60 °C
Dry cleaning resistance	very good
Heat resistance	90 °C
Steam resistance	good
Appearance	White powder
Ratio of renewable raw materials	0 %
Biodegradability	no
Fusing conditions with flow-through-press	Lamination temperature: 110 – 145 °C Pneumatic pressure: 3 – 5 N/cm ² Time: 10 – 15 seconds
Application	Interlinings with fusing conditions and low viscosity at good fastness profile; siliconized fabrics; in paste dot coating as crosslinkable thermoplast as base dot in doubledot process or single dot in direct lamination – outstanding fastnesses are reached

Recipe recommendation Vernetzbare Copolyamid Druckpaste

Crosslinkable Paste

Water / H ₂ O	55 kg
ROWAFLEX® DF 2	0.2 kg
ROWAFLEX® X 600	3 kg
ROWALIT® 200-63, 0-80	30 kg
ROWAFLEX® TH 3	0.4 kg
ROWAFLEX® X 100	10 kg

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.

Certified Quality
Management System



Version: 28.06.2022

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.

ROWAK AG
Hadlaubstraße 66 Tel +41 43 300 53 33 www.rowak.ch
CH 8006 Zürich Fax +41 43 300 53 35 info@rowak.ch

Certified Quality
Management System

ROWAK AG
Schmittenstraße 21
D-79771 Klettgau

