

ROWALIT 300-1/18-150

Ethylene-Vinyl-Acetate Powder

Type	EVA
Chemical character	Ethylene-Vinyl-Acetate
Melting range	75 – 79 °C DSC
Melt Flow Index	150 g / 10 Min. (MFI 190°C / 2,16 kg)
Density	937 kg/m ³
VA-Content	18
Powder sizes	Scatter Granules
Washing resistance	40 °C
Heat resistance	40 °C
Hand iron	yes
Appearance	White powder
Fusing conditions with flow-through-press	Lamination temperature: 90 – 95 °C Pneumatic pressure: 2 – 4 N/cm ² Time: 3 – 5 seconds

Version: 10.01.2025

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.