

Ethylene-Vinyl-Acetate Powder

03.08.2026
info@rowak.ch



Product name	ROWALIT™ 300-1/33-25
Type	EVA
Chemical character	Ethylene-Vinyl-Acetate
Melting range	59 – 65 °C DSC
Melt Flow Index	25 g / 10 Min. (MFI 190°C / 2,16 kg)
Density	96 kg/m ³
VA-Content	33 %
Powder sizes	Scatter (100 – 500 µm) Granules
Washing resistance	40 °C
Heat resistance	40 °C
Hand iron	yes
Appearance	White powder
Fusing conditions with flow-through-press	Lamination temperature: 75 – 82 °C Pneumatic pressure: 2 – 4 N/cm ² Time: 3 – 5 Sekunden

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit Unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

www.rowak.ch