ROWALIT® 300-1/33-25

Ethylene-Vinyl-Acetate Powder

Type	EVA
Chemical character	Ethylene-Vinyl-Acetate
Melting range	59 – 65 °C DSC
Melt Flow Index	25 g / 10 Min. (MFI 190°C / 2,16 kg)
Density	96 kg/m³
VA-Content	33
Powder sizes	Scatter (100 – 500 µm) Granules
Washing resistance	40 °C
Heat resistance	40 °C
Hand iron	yes
Appearance	White powder
Fusing conditions with flow-through-press	Lamination temperature: 75 – 82 °C Pneumatic pressure: 2 – 4 N/cm² Time: 3 – 5 seconds

Version: 26.04.2022

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.
All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.

Certified Quality Management System
TÜV SÜD ISO 9001

ROWAK AG
Hadlaubstraße 66
CH 8006 Zürich
Tel +41 43 300 53 33
Fax +41 43 300 53 35
www.rowak.ch
info@rowak.ch

ROWAK AG
Schmittenstraße 21
D-79771 Klettgau