

Product name	ROWALIT™ 400-1
Type	Copolyester
Chemical character	Copolyester
Melting range	118 – 123 °C DSC
Melt Flow Index	30 g / 10 Min. (MFI 160°C / 2,16 kg)
Powder sizes	Pastedot (0 – 63 µm, 0 – 80 µm) Doubledot (80 – 160 µm, 80 – 200 µm) Powderdot (0 – 160 µm) Scatter (100 – 500 µm) Granules Other sizes upon request
Washing resistance	80 °C
Dry cleaning resistance	good
Heat resistance	100 °C
Hand iron	no
Enzyme washing	no
Steam resistance	gut
Appearance	White powder
Ratio of renewable raw materials	0 %
Biodegradability	no

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit Unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

www.rowak.ch

Fusing conditions with flow-through-press

Lamination temperature: 130 - 150 °C
Pneumatic pressure: 3 - 5 N/cm²
Time: 10 - 12 Sekunden

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit Unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

www.rowak.ch

rowak
SWISS ENGINEERED ADHESIVES

ROWAK AG
Hadlaubstrasse 66
8006 Zürich
Switzerland

ROWAK AG
Schmittenstrasse 21
79771 Klettgau-Griessen
Germany

