

ROWALIT 400-14

Copolyester Powder

Type	Copolyester
Chemical character	Copolyester
Melting range	177 – 186 °C DSC
Melt Flow Index	110 g / 10 Min. (MFI 190°C / 2,16 kg)
Powder sizes	Pastedot (0 – 80 µm) Doubledot Scatter Granules Other sizes upon request
Washing resistance	90 °C
Dry cleaning resistance	good
Heat resistance	140 °C
Typical application	Filtration media for gasoline
Hand iron	no
Steam resistance	yes
Appearance	White powder
Ratio of renewable raw materials	40 %
Biodegradability	no
Fusing conditions with flow-through-press	Lamination temperature: 210 – 230 °C Pneumatic pressure: 3 – 10 N/cm ² Time: 12 – 20 seconds
Application	Bonding of substrates of filtration media of Lubricants, Oils and Gasoline

Version: 10.01.2025

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.