

## **ROWALIT® 400-20**

## Copolyester Powder

T	Canalyzatan
Туре	Copolyester
Chemical character	Copolyester
Melting range	70 – 85 °C DSC
Melt Flow Index	150 g / 10 Min. (MFI 160°C / 2,16 kg)
Powder sizes	Pastedot Doubledot Powderdot Scatter Granules
Washing resistance	40 °C
Dry cleaning resistance	low
Heat resistance	70 °C
Hand iron	yes
Steam resistance	low
Stone-wash resistance	no
Appearance	White powder
Ratio of renewable raw materials	0 %
Biodegradability	no
Fusing conditions with flow-through-press	Lamination temperature: 90 – 120 °C Pneumatic pressure: 2 – 4 N/cm² Time: 10 – 15 seconds
Properties	ROWALIT 400-20 is a low fusing temperature, flexible and fast crystallizing thermoplastic copolyester adhesive that provides strong bonds to a wide variety of substrates.
V	

Version: 31.07.2023

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.

Certified Quality Management System

