

ROWALIT 400-32

Copolyester Powder

Type	Copolyester
Chemical character	Copolyester
Melting range	140 – 160 °C DSC
Melt Flow Index	5.5 g / 10 Min. (MFI 190°C / 2,16 kg)
Powder sizes	Pastedot (0 – 80 µm) Doubledot (80 – 200 µm) Powderdot (0 – 200 µm) Scatter (100 – 500 µm) Granules Other sizes upon request
Washing resistance	60 °C
Heat resistance	130 °C
Hand iron	no
Steam resistance	N/A
Appearance	White powder
Ratio of renewable raw materials	0 %
Biodegradability	no
Fusing conditions with flow-through-press	Lamination temperature: 140 – 160 °C Pneumatic pressure: 3 – 5 N/cm ² Time: 10 – 20 seconds
Properties	Highly transparent and glossy Polyester
Application	Technical Bondings

Version: 01.12.2025

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.