

ROWALIT FS-9

Modified copolymer flame-retardant Powder

Type	Flame-retardant Powders
Chemical character	Copolymer Blend
Melting range	110 – 120 °C DSC
Vicat softening point	96 – 96 °C (DIN 53460, ISO 306)
Powder sizes	Scatter Other sizes upon request
Heat resistance	95 °C
Appearance	White powder
Fusing conditions with flow-through-press	Lamination temperature: 130 – 160 °C Pneumatic pressure: 3 – 5 N/cm ² Time: 10 – 20 seconds

Version: 10.01.2025

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

All information provided is based on our experience and current know-how but is given without guarantee and obligation. Recommendations on the application and use of our products should be adapted to the particular conditions and other materials employed.