

Product name	ROWALIT™ H20
Type	LDPE
Chemical character	Low-Density-Polyethylene
Melting range	104 – 108 °C DSC
Vicat softening point	82 – 86 °C (DIN 53460, ISO 306)
Melt Flow Index	20 g / 10 Min. (MFI 190°C / 2,16 kg)
Density	918 kg/m ³
Powder sizes	Granules Other sizes upon request
Washing resistance	60 °C
Heat resistance	80 °C
Steam resistance	good
Appearance	White powder
Ratio of renewable raw materials	0 %
Biodegradability	nein
Fusing conditions with flow-through-press	Lamination temperature: 130 – 150 °C Pneumatic pressure: 3 – 5 N/cm ² Time: 10 – 15 Sekunden

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit Unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

www.rowak.ch