

Copolyester Powder

03.08.2026
info@rowak.ch

Product name	ROWALIT™ PET-32
Type	Copolyester
Chemical character	Copolyester
Melting range	140 – 160 °C DSC
Melt Flow Index	5.5 g / 10 Min. (MFI 190°C / 2,16 kg)
Powder sizes	Pastedot (0 – 80 µm) Doubledot (80 – 200 µm) Powderdot (0 – 200 µm) Scatter (100 – 500 µm) Granules Other sizes upon request
Washing resistance	60 °C
Heat resistance	100 °C
Hand iron	no
Steam resistance	N/A
Appearance	White powder
Ratio of renewable raw materials	0 %
Biodegradability	no
Fusing conditions with flow-through-press	Lamination temperature: 160 – 190 °C Pneumatic pressure: 3 – 5 N/cm ² Time: 10 – 20 Sekunden
Properties	Highly transparent and glossy Polyester

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit Unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

www.rowak.ch

Application

Technical Bondings

Die vorstehenden Angaben entsprechen dem derzeitigen Stand unserer Erkenntnisse und Erfahrungen. Wir beraten Sie damit Unverbindlich und bitten Sie, alle Angaben über die Verwendung unserer Produkte auf die bei Ihnen vorliegenden Verhältnisse abzustimmen und den verwendeten Materialien anzupassen.

www.rowak.ch